



LEED STATEMENT

MR CREDIT 4 Recycled Content

Average % on Primary System Components

Fellert Fiberglass Board: approximately **60%** *post consumer* recycled content.

Fellert Acoustical Plaster: approximately **30%** *post consumer* content—**recycled cotton material**.

IEQ CREDIT 4 Low Emitting Materials

The Fellert acoustical plaster was tested for VOC and IAQ:

- low VOC as per ASTM D3960
"Determination of Volatile Organic Compound (VOC) Content in Paints and Related Coatings"

IEQ CREDIT 7 Thermal Insulating R Value

Thermal Conductivity ASTM C-177 @ 75 F on 6.0 PCF 0.22

1" Fellert Fiberglass Board **4.55 R Value**
1.5" Fellert Fiberglass Board **6.82 R Value**

IEQ CREDIT 8 Light Reflectance

0.93 As per ASTM E1477-98a

042912SA

Fellert International AB
Kyrkängsgatan 6
503 38 Borås, Sweden
Tel: 46 33 4302202